

This listing of claims will replace all prior versions and listings of claims in the application:

Listing of Claims:

1. *(Currently Amended)* A method of producing a frangible fiberglass insulation batt, the method comprising the acts of

providing a fluid-reservoir tray formed to include a fluid-discharge aperture opening toward a conveyor

passing a fiberglass insulation blanket through an interval cutter to cut the fiberglass insulation blanket along a cut line to form two side-by-side strips separated by a series of intermittent gaps to form a frangible plane extending along the cut line, wherein the act of passing comprises the acts of discharging a flow of high-pressure fluid to intercept and penetrate the fiberglass insulation blanket along the cut line to form a gap in the fiberglass insulation blanket as the fiberglass insulation blanket is passed through the interval cutter and interrupting the flow of high-pressure fluid intermittently as the fiberglass insulation blanket is passed through the interval cutter to divert the flow of high-pressure fluid from intercepting and penetrating the fiberglass insulation blank intermittently to establish the series of intermittent gaps in the fiberglass insulation blanket and cause the diverted flow of high-pressure fluid to pass into a fluid-reservoir tray located above the insulation blanket to block the flow of high-pressure fluid.

2. *(Previously Presented)* The method of claim 1, wherein the act of passing includes the act of moving the fiberglass insulation blanket in a conveyance direction relative to the interval cutter and the act of interrupting includes the acts of moving a fluid blocker comprising a plate located above the fluid-reservoir tray and formed to include a first fluid-discharge slot associated with a first gap formed in the insulation fiberglass blanket and a second fluid-discharge slot associated with a second gap formed in the fiberglass insulation blanket relative to the fiberglass insulation blanket to intercept the flow of high-pressure fluid discharged toward the fiberglass insulation blanket to block the flow of high-pressure fluid from intercepting the fiberglass insulation blanket.

3. *(Previously Presented)* A method of producing a frangible fiberglass insulation batt, the method comprising the acts of

passing a fiberglass insulation blanket through an interval cutter to cut the fiberglass insulation blanket along a cut line to form two side-by-side strips separated by a series of intermittent gaps to form a frangible plane extending along the cut line, wherein the act of passing comprises the acts of discharging a flow of high-pressure fluid to intercept and penetrate the fiberglass insulation blanket along the cut line to form a gap in the fiberglass insulation blanket as the fiberglass insulation blanket is passed through the interval cutter, interrupting the flow of high-pressure fluid intermittently as the fiberglass insulation blanket is passed through the interval cutter to divert the flow of high-pressure fluid from intercepting and penetrating the fiberglass insulation blank intermittently to establish the series of intermittent gaps in the fiberglass insulation blanket, and moving the fiberglass insulation blanket in a conveyance direction relative to the interval cutter, and wherein the act of interrupting includes the acts of moving a fluid blocker relative to the fiberglass insulation blanket to intercept the flow of high-pressure fluid discharged toward the fiberglass insulation blanket to block the flow of high-pressure fluid from intercepting the fiberglass insulation blanket and oscillating the fluid blocker along a path relative to the fiberglass insulation blanket between a first position placing a blocking surface included in the fluid blocker in a location between an outlet discharging the flow of high-pressure fluid and the fiberglass insulation blanket to cause the flow of high-pressure fluid to impinge upon the blocking surface and a second position allowing the flow of high-pressure fluid to pass through a slot formed in the fluid blocker to intercept and penetrate the fiberglass insulation blanket to establish a first in the series of intermittent gaps.

4. *(Original)* The method of claim 3, wherein the path along which the fluid blocker oscillates is perpendicular to the conveyance direction in which the fiberglass insulation blanket is moved.

5. *(Original)* The method of claim 3, wherein the act of interrupting further includes the act of collecting high-pressure fluid after impingement of said high-pressure fluid on the blocking surface of the fluid blocker in a reservoir located above the fiberglass insulation blanket.

6. *(Original)* The method of claim 3, wherein the act of interrupting further includes the act of conducting high-pressure fluid that has impinged upon the blocking surface away from the fiberglass insulation blanket.

7. *(Previously Presented)* A method of producing a frangible fiberglass insulation batt, the method comprising the acts of

passing a fiberglass insulation blanket through an interval cutter to cut the fiberglass insulation blanket along a cut line to form two side-by-side strips separated by a series of intermittent gaps to form a frangible plane extending along the cut line, wherein the act of passing comprises the acts of discharging a flow of high-pressure fluid to intercept and penetrate the fiberglass insulation blanket along the cut line to form a gap in the fiberglass insulation blanket as the fiberglass insulation blanket is passed through the interval cutter, interrupting the flow of high-pressure fluid intermittently as the fiberglass insulation blanket is passed through the interval cutter to divert the flow of high-pressure fluid from intercepting and penetrating the fiberglass insulation blank intermittently to establish the series of intermittent gaps in the fiberglass insulation blanket, and moving the fiberglass insulation blanket in a conveyance direction relative to the interval cutter, and wherein the act of interrupting includes the acts of moving a fluid blocker relative to the fiberglass insulation blanket to intercept the flow of high-pressure fluid discharged toward the fiberglass insulation blanket to block the flow of high-pressure fluid from intercepting the fiberglass insulation blanket and oscillating the fluid blocker along a path relative to the fiberglass insulation blanket between a first position placing a blocking surface included in the fluid blocker between an outlet discharging the flow of high-pressure fluid and the fiberglass insulation blanket to cause the flow of high-pressure fluid to impinge upon the blocking surface, a second position allowing the flow of high-pressure fluid to pass through a first fluid-discharge slot formed in the fluid blocker to intercept and penetrate the fiberglass insulation blanket to establish a first in the series of intermittent gaps, and a third position allowing the flow of high-pressure fluid to pass through a second fluid-discharge slot formed in the fluid blocker to intercept and penetrate the fiberglass insulation blanket to establish a second in the series of intermittent gaps.

8. *(Original)* The method of claim 7, wherein the fluid blocker is configured to locate the blocking surface between the first and second fluid-discharge slots.

9. *(Original)* The method of claim 7, wherein the act of oscillating includes the acts of, in series, urging the fluid blocker to move in a first direction from the first position to the second position, urging the fluid blocker to move in an opposite second direction from the second position to the first position and then to the third position, and urging the fluid blocker to move in the first direction from the third position to the first position.

10. *(Original)* The method of claim 7, wherein the path along which the fluid blocker oscillates is perpendicular to the conveyance direction in which the fiberglass insulation blanket is moved.

11. *(Original)* The method of claim 7, wherein the act of interrupting further includes the act of collecting high-pressure fluid after impingement of said high-pressure fluid on the blocking surface of the fluid blocker in a reservoir located above the fiberglass insulation blanket.

12. *(Original)* The method of claim 7, wherein the act of interrupting further includes the act of conducting high-pressure fluid that has impinged upon the blocking surface away from the fiberglass insulation blanket.

13. *(Previously Presented)* A method of producing a frangible fiberglass insulation batt, the method comprising the acts of

passing a fiberglass insulation blanket through an interval cutter to cut the fiberglass insulation blanket along a cut line to form two side-by-side strips separated by a series of intermittent gaps to form a frangible plane extending along the cut line, wherein the act of passing comprises the acts of discharging a flow of high-pressure fluid to intercept and penetrate the fiberglass insulation blanket along the cut line to form a gap in the fiberglass insulation blanket as the fiberglass insulation blanket is passed through the interval cutter and interrupting the flow of high-pressure fluid intermittently as the fiberglass insulation blanket is passed through the interval cutter to divert the flow of high-pressure fluid from intercepting and penetrating the fiberglass insulation blank intermittently to establish the series of intermittent gaps in the fiberglass insulation blanket, wherein the act of interrupting includes the acts of, in series, locating a fluid blocker formed to include elongated first and second fluid-discharge slots and a blocking surface located between the elongated first and second fluid-discharge slots in a fluid-blocking position to cause the flow of high-pressure fluid discharged toward the fiberglass

insulation blanket to impinge upon the blocking surface to block the flow of high-pressure fluid from intercepting and penetrating the fiberglass insulation blanket, urging the fluid blocker to move in a first direction from the fluid-blocking position to a first outer limit position to allow the flow of high-pressure fluid to flow through the elongated first fluid-discharge slot to form a leading section of a first in the series of intermittent gaps, urging the fluid blocker to move in an opposite second direction from the first outer limit position toward the fluid-blocking position to allow the flow of high-pressure fluid to continue to flow through the first fluid-discharge slot to form a trailing section of the first in the series of intermittent gaps, urging the fluid blocker to continue to move in the opposite second direction to the fluid-blocking position to cause the flow of high-pressure fluid to impinge upon the blocking surface to block the flow of high-pressure fluid from intercepting and penetrating the fiberglass insulation blanket, urging the fluid blocker to continue to move in the opposite second direction from the fluid-blocking position to a second outer limit position to allow the flow of high-pressure fluid to flow through the elongated second fluid-discharge slot to form a leading section of a second in the series of intermittent gaps, urging the fluid blocker to move in the first direction from the second outer limit position toward the fluid-blocking position to allow flow of high-pressure fluid to continue to flow through the second fluid-discharge slot to form a trailing section of the second in the series of intermittent gaps, and urging the blocker to continue to move in the first direction to the fluid-blocking position to cause the flow of high-pressure fluid to impinge upon the blocking surface to block the flow of high-pressure fluid from intercepting and penetrating the fiberglass insulation blanket.

14. *(Original)* The method of claim 13, wherein each of the first direction and the opposite second direction is perpendicular to the conveyance direction.

15. *(Original)* The method of claim 13, wherein the act of interrupting further includes the act of interrupting further includes the act of collecting high-pressure fluid after impingement of said high-pressure fluid on the blocking surface of the fluid blocker in a reservoir located above the fiberglass insulation blanket.

16. *(Original)* The method of claim 13, wherein the act of interrupting further includes the act of interrupting further includes the act of conducting high-pressure fluid that has impinged upon the blocking surface away from the fiberglass insulation blanket.

17. *(Previously Presented)* A method of producing a frangible fiberglass insulation batt, the method comprising the acts of

passing a fiberglass insulation blanket through an interval cutter to cut the fiberglass insulation blanket along a cut line to form two side-by-side strips separated by a series of intermittent gaps to form a frangible plane extending along the cut line, wherein the act of passing comprises the acts of discharging a flow of high-pressure fluid to intercept and penetrate the fiberglass insulation blanket along the cut line to form a gap in the fiberglass insulation blanket as the fiberglass insulation blanket is passed through the interval cutter and interrupting the flow of high-pressure fluid intermittently as the fiberglass insulation blanket is passed through the interval cutter to divert the flow of high-pressure fluid from intercepting and penetrating the fiberglass insulation blank intermittently to establish the series of intermittent gaps in the fiberglass insulation blanket, and further comprising the act of then passing the two side-by-side strips through a curing oven to expose the strips to a predetermined fiberglass curing heat extant in the curing oven to cause binder extant in the fiberglass insulation blanket to polymerize to establish a frangible bridge spanning each of the series of intermittent gaps in the fiberglass insulation blanket.

18-19. *(Canceled)*.

20. *(Currently Amended)* A method of producing a frangible fiberglass insulation batt, the method comprising the acts of

moving ~~[[a]]~~ an uncured fiberglass insulation blanket having a binder extant in the fiberglass insulation blanket in a conveyance direction and applying a first flow of high-pressure fluid to the moving fiberglass insulation blanket intermittently to establish a first series of intermittent gaps cooperating to define a first frangible plane in the fiberglass insulation blanket, and

moving the fiberglass insulation blanket through a curing oven after the applying act to expose the fiberglass insulation blanket to a predetermined fiberglass curing heat extant in the curing oven to cause binder extant in the fiberglass insulation blanket to polymerize to establish a frangible bridge spanning each of the first series of intermittent gaps.

21. *(Previously Presented)* A method of producing a frangible fiberglass insulation batt, the method comprising the acts of

moving a fiberglass insulation blanket in a conveyance direction,
providing a fluid-reservoir tray supported in an elevated position above the conveyor and formed to include a fluid-discharge aperture opening toward the conveyor,
aiming a flow of high-pressure fluid discharged from a fluid discharger to pass through the fluid-discharge opening formed in the fluid-reservoir tray and toward the fiberglass insulation blanket, and
oscillating a fluid blocker for movement in a space located between the fluid discharger and the fluid-reservoir tray relative to the flow of high-pressure fluid through a movement cycle comprising, in series, a first position interrupting the flow of high-pressure fluid, a second position allowing the flow of high-pressure fluid to intercept and penetrate the moving fiberglass insulation blanket to establish a first gap in a series of intermittent gaps, the first position, and a third position allowing the flow of high-pressure fluid to intercept and penetrate the moving fiberglass insulation blanket to establish a second gap in the series of intermittent gaps.

22. *(Original)* The method of claim 21, wherein the oscillating act includes the act of repeating the movement cycle to establish additional gaps in the series of intermittent gaps to define a frangible plane extending along the fiberglass insulation blanket.

23-26. *(Canceled)*.